

Apeiron's

Revolutionary 2-Step Terrazzo Resurfacing and Wet Polishing Procedures

Step 1 — Scratch Removal Discs II (SRD II):

Thoroughly strip the floor to completely remove surface coatings.



Hone the surface with cool water and **Apeiron's SRD II** attached to the **Rigid Disk Holder (RDH)**.



Honing process time is 30 seconds per sq. ft. 8 mins for 16 sq. ft. Keep surface wet.



Vacuum the slurry and rinse with **Apeiron's Stone Wash**.



Step 2 — Wet Polishing (Maintenance Procedures):

Pour 1 oz. Wet Polish and 4 oz. of water directly onto the floor.



Buff approximately 16-20 sq. ft. with mixture & **Dia-Poly FP Pad** with red wear indicators facing the floor.



Buff for 30 sec. per sq. ft. 8 mins. for 16 sq. ft. Keep mixture wet at all times.



Wet vacuum to remove the slurry residue. Damp mop rinse with **Apeiron's Stone Wash**.



Repeat application if higher gloss is desired

- Protect with Apeiron's Impregnator Seal



- Clean daily with Apeiron's Stone Wash



- Maintain gloss with Apeiron's Marble Shake

